

**Technisches Datenblatt/  
Technical data sheet**

**Feuerfester Kleber IND-70700-FFKL**

Körnung/Granulation	mm	0 – 1	
Werkstoffbasis/Material basis		Schamotte	
Typische chemische Analyse/ Typical chemical analysis (DIN EN ISO 12677, RFA)	%	SiO <sub>2</sub>	15,40
		Al <sub>2</sub> O <sub>3</sub>	71,60
		FE <sub>2</sub> O <sub>3</sub>	0,30
		CaO+MgO	0,26
		Na <sub>2</sub> O+K <sub>2</sub> O	6,10
Anwendungsgrenze/ Limit of application	°C	1000	
Lagerfähigkeit/ Storability	Monate/ month	24	
Gefahrguthinweise/ Dangerous goods notes	siehe Sicherheitsdatenblatt/ see safety data sheet		

*Obwohl bei der Zusammenstellung dieser Information äußerste Sorgfalt angewandt wurde, wird diese ohne Gewähr herausgegeben. Wir lehnen jegliche Verantwortung für einen Verlust, eine Beschädigung oder Kosten ab, die durch einen darin enthaltenen Fehler entstehen. Da der Einsatz des Produkts nicht unserer Kontrolle unterliegt, ist der Anwender für die Eignung des Produktes in jedem Einzelfall selbst verantwortlich.*

*Although every care has been taken in compiling this information, it is provided "as is" without warranty of any kind. We disclaim any responsibility for any loss, damage or expense arising from any defect contained herein. As the use of the product is not under our control, the user is responsible for the suitability of the product in each individual case.*

Stand 04/2026

Seite 1 von 1